

フェライト磁石特性表

FERRITE MAGNETS

材質 Type	残留磁束密度 Remanence Br		保磁力 Coercivi Force				最大エネルギー積 Energy Product (BH)max	
	kGs	mT	HcB Normal Coercivity		HcJ Intrinsic Coercivity		KJ/m ³	MGOe
			kOe	kA/m	kOe	kA/m		
Y10T(=C1)	2.00/2.18	200/218	1.57/1.82	125/145	2.64/3.14	210/250	6.5/8.0	0.8/1.0
Y25	3.60/3.70	360/370	1.70/1.88	135/150	1.76/2.14	140/170	22.5/25.3	2.8/3.2
Y30(=C5)	3.80/3.85	380/385	2.40/2.64	191/210	2.50/2.51	199/220	26.0/28	3.4/3.7
Y30BH	3.80/3.90	380/390	2.80/2.95	223/235	2.90/3.08	231/245	27.0/30.0	3.4/3.7
Y33	4.10/4.20	410/420	2.77/2.95	220/235	2.83/3.01	225/240	31.5/33.0	4.0/4.2
Y35	4.00/4.10	400/410	2.20/2.45	175/195	2.26/2.51	180/200	30.0/32.0	3.8/4.0
C8(=C8A)	3.85/3.90	385/390	2.95/3.20	235/255	3.05/3.33	242/265	27.8/30.0	3.5/3.7
C10	4.00/4.10	400/410	3.62/3.77	288/300	3.51/3.60	280/287	30.4/31.9	3.8/4.0



磁石加工・磁石着磁・磁石検査・磁石販売等、磁石の事ならお任せください！

有限会社前林製作所

〒360-0017 埼玉県熊谷市小曾根 1390-2

TEL 048-523-0283 FAX 048-521-8324

URL <http://maebayashi.co.jp>

e-mail info@maebayashi.co.jp